

**TDS 0610**

REVIEW: 04/2015

Standards: AWWA C-210\_03

**Rekotar DHS 220**

Component A: 220.0995 (Black), 220.0848 (Brown)

Component B: 824.0900



Rekotar DHS 220 uses specially selected raw materials, so that is specially formulated to fresh water tanks.

**TECHNICAL CHARACTERISTICS****TYPE**

Polyamide epoxy coal tar coat, two pack system.

**USAGE**

Recommended as a coating for industrial water tanks, salt water, crude oil, dry bulk, etc. Consult the technical department to verify the resistance to the desired products.

**TECHNICAL INFORMATIONS**

<b>COLOR</b>	Black and Brown		
<b>FINISH</b>	Matt		
<b>VOLUME SOLIDS</b>	70% ± 2	According to ISO 3233	
<b>WEIGHT PER LITER</b>	1,420 ± 0,05 g/ml	According to ASTM D 1475	
<b>FLASH POINT</b>	24 °C		
<b>MIXING RATIO</b>		Weight	Volume
	<b>Comp. A</b>	100,0	3,0
	<b>Comp. B</b>	24,3	1,0
<b>POT LIFE (25°C)</b>	2 h		
<b>INDUCTION TIME</b>	5 min		
<b>THEORETICAL SPREADING RATE</b>	1,75 m <sup>2</sup> /l - 400 µm		
<b>WET THICKNESS</b>	572 µm		
<b>DRY THICKNESS</b>	400 µm		
<b>DRYING TIME, for 400 µm</b>		25°C	
		Minimum	Maximum
	<b>Touch</b>		3 h
	<b>Handle</b>		8 h
	<b>Recoat</b>	18 h	72 h
<b>ENVIRONMENTAL CONDITIONS</b>	<b>Temperature</b>	Should be between 0 to 40°C. For temperatures below 10°C, add 1,12% in volume of curing agent 870.0576.	
	<b>Relative Humidity</b>	Between 30 and 85%	
	<b>Dew Point</b>	Surface temperature is at least 3°C above dew point	
	<b>Thinner</b>	420.0000	
<b>APPLICATION</b>	<b>Brush</b>	It is not necessary dilution. This method must be used only for retouch and backing of welding cords and corners.	
	<b>Roller</b>	Dilute up to 10% (vol.) with recommended thinner. Must be used solvent resistant roller (sheep wool). The wool must be cutted (small size) to avoid blistering during the application.	
	<b>AirLess Spray Gun</b>	Dilute up to 10% (vol.) with recommended thinner. Use nozzles between 23 to 31 and pump pressure between 140 to 175 kgf/cm <sup>2</sup> (2000 to 2500 psi).	

**TDS 0610**

REVIEW: 04/2015

Standards: AWWA C-210\_03

**Rekotar DHS 220**

Component A: 220.0995 (Black), 220.0848 (Brown)

Component B: 824.0900



<b>SURFACE PREPARATION</b>	<b>Direct over carbon steel</b>	Blast cleaning ISO 8501-1 Sa 2 ½. The surface must be dry, free of contaminants such as salt deposits, oil, grease, fat, dust and other kind of contaminants.
	<b>Recommended Primers</b>	Not applicable
	<b>Coated Surfaces</b>	The surface must be clean and free of contaminants as oils, fat, grease and dust. Must not present peeling's areas. Proceed light sanding (220) to break the gloss.
	<b>Recommended TopCoat</b>	Not applicable

**SHELF LIFE** 12 months

**UN NUMBER** 1263

**HAZARD NUMBER** 33

---

**IMPORTANT RECOMMENDATIONS**


---

1. The practical spreading rate of the product varies according to the applied thickness, application method and techniques, type and rugosity of the surface and ambient conditions.
2. The weight/l, viscosity and drying values were obtained in laboratory at a temperature of 25°C. At an altered temperature, the results might be different from the specified ones.
3. Low temperatures increase the curing time. At temperatures below 10°C, please contact our technical department.
4. Important: add curing agent to component A and homogenize, then mix components A and B for 5 minutes using mechanical agitator. Additivation is NOT recommended for immersion products. Additivation reduces pot life.
5. Pot life is shortened by higher temperature and by the increase of catalyzed volume.

---

**SAFETY PRECAUTIONS**


---

1. Improper use and handling of this product can be hazardous to health and cause fire or explosion. Do not use it without first taking all appropriate measures to prevent property damage and injuries.
  2. Storage: keep the product in sheltered, well-ventilated areas. Maximum temperature: 40° C. Must not be directly exposed to the sun.
  3. Flammable: flammable product, which must be kept distant from ignition sources, and do not smoke nearby.
  4. Inhalation: Avoid breathing vapors, keeping proper ventilation during application and drying.
  5. Handling: wear proper protective clothing and masks, goggles, etc. Do not eat or drink nor allow children and animals to be near the application area.
-



---

## HEALTH HAZARDS

---

1. Skin contact: wash affected area thoroughly with neutral soap.
2. Clothing contact: remove clothing and wash it.
3. Leakage: Isolate the area, and do not smoke nearby. If large quantity leaked in confined area, wear protective masks. Do not inhale vapors. Stop leakage with sand, sawdust or soil, and transfer liquid and solid to separated recipients for disposal.
4. Fire: protect non-affected recipients with water spray. Extinguish fire using carbon dioxide, foam or dry chemical.
5. Eyes contact: flush eyes with large amounts of clean water for at least 10 minutes, and get medical attention immediately.

IMPORTANT: For further information consult the product MSDS (Material Safety Data Sheet).

---