



Rekotar DKC 221 Especial uses specially selected raw materials based on special epoxy coal tar, showing excellent chemical and abrasion resistance, and a high resistance to cathodic protection. This is a high build, high solids and an ecological product, low volatile organic compounds (low VOC).

TECHNICAL CHARACTERISTICS

TYPE

Epoxy primer, two pack system

USAGE

structures, concrete coating, pier poles, etc. It is also indicated for columns, coamings, offshore structures. Recommended for coating tanks with industrial water and sea water (internal and external).

TECHNICAL INFORMATION

COLOR	Brown and Black		
FINISH	Semiglossy		
VOLUME SOLIDS	78 % ± 2	According to ISO 3233	
WEIGHT PER LITER	1,400 ± 0,05 g/ml	According to ASTM D 1475	
FLASH POINT	32°C		
MIXING RATIO		Weight	Volume
	Comp. A	100,0	5,0
	Comp. B	15,0	1,0
POT LIFE (25°C)	3 h		
INDUCTION TIME	10 min		
THEORETICAL SPREADING RATE	4,3 m ² /l - 180 µm 1,95 m ² /l - 400 µm		
WET THICKNESS	231 µm to 513 µm		
DRY THICKNESS	180 µm to 400 µm		
DRYING TIME, for 180 µm	25°C		
		Minimum	Maximum
	Touch		3 h
	Handle		18 h
	Recoat	16 h	72 h
ENVIROMENTAL CONDITIONS	Temperature	Should be between 0 to 40°C	
	Relative Humidity	Between 30 to 85%	
	Dew Point	Surface temperature is at least 3°C above dew point	
	Thinner	420.0000	
APPLICATION	Brush	It is not necessary dilution. This method must be used only for retouch and backing of welding cords and corners.	
	Roller	Dilute up to 20% (vol.) with recommended thinner. Must be used solvent resistant roller (sheep wool). The wool must be cutted (small size) to avoid blistering during the application.	
	AirLess Spray Gun	Dilute up to 20% (vol.) with recommended thinner. Use nozzles between 23 to 29 and pump pressure between 175 to 210 kgf/cm ² (2500 to 3000 psi).	



SURFACE PREPARATION	Direct over carbon steel	Blast cleaning ISO 8501-1 Sa 2 ½ (minimum) and mechanical treatment St 3 (for small areas). The surface must be dry, free of contaminants such as salt deposits, oil, grease, fat, dust and other kind of contaminants.
	Recommended Primers	Revrans SPN 520 and Revran SEL 639. For other primers, please contact our Consultants.
	Coated Surfaces	The surface must be clean and free of contaminants as oils, fat, grease and dust. Must not present peeling's areas. Proceed light sanding (220) to break the gloss.
	Recommended TopCoat	Not applicable

SHELF LIFE 12 months

UN NUMBER 1263

HAZARD NUMBER 33

IMPORTANT RECOMMENDATIONS

1. The practical spreading rate of the product varies according to the applied thickness, application method and techniques, type and rugosity of the surface and ambient conditions.
2. The weight/l, viscosity and drying values were obtained in laboratory at a temperature of 25°C. At an altered temperature, the results might be different from the specified ones.
3. Low temperatures increase drying time. Contact our Consultants for temperatures below 10°C.
4. The film color might change if submitted to UV exposure and/or immersion, without modifying its physical-chemical properties.
5. Pot life is shortened by higher temperature, and by the increase of catalyzed volume.

SAFETY PRECAUTIONS

1. Improper use and handling of this product can be hazardous to health and cause fire or explosion. Do not use it without first taking all appropriate measures to prevent property damage and injuries.
 2. Storage: keep the product in sheltered, well-ventilated areas. Maximum temperature: 40° C. Must not be directly exposed to the sun.
 3. Flammable: flammable product, which must be kept distant from ignition sources, and do not smoke nearby.
 4. Inhalation: Avoid breathing vapors, keeping proper ventilation during application and drying.
 5. Handling: wear proper protective clothing and masks, goggles, etc. Do not eat or drink nor allow children and animals to be near the application area.
-



HEALTH HAZARDS

1. Skin contact: wash affected area thoroughly with neutral soap.
2. Clothing contact: remove clothing and wash it.
3. Leakage: Isolate the area, and do not smoke nearby. If large quantity leaked in confined area, wear protective masks. Do not inhale vapors. Stop leakage with sand, sawdust or soil, and transfer liquid and solid to separated recipients for disposal.
4. Fire: protect non-affected recipients with water spray. Extinguish fire using carbon dioxide, foam or dry chemical.
5. Eyes contact: flush eyes with large amounts of clean water for at least 10 minutes, and get medical attention immediately.

IMPORTANT: For further information consult the product MSDS (Material Safety Data Sheet).
