

Revran DST FAST CURE MDB 870 uses specially selected raw materials, showing high build, high solids and low VOC. Fast drying and long recoating interval. The product has excellent adhesion, good mechanical resistance, great penetrating power and is applicable on substrates treated mechanically. Contains zinc phosphate anticorrosive pigment.

#### TECHNICAL CHARACTERISTICS

##### TYPE

Epoxy resin, dual function. Two pack system.

##### USAGE

In carbon steel substrate, especially suitable for steel structures, providing protection to steel. Also suitable for outdoor tanks, pipes, silos and other equipment new or maintenance.

#### TECHNICAL INFORMATION

<b>COLOR</b>	White	Other colors, please consult.	
<b>FINISH</b>	Satin		
<b>VOLUME SOLIDS</b>	75% ± 2	According to ISO 3233	
<b>WEIGHT PER LITER</b>	1,500 ± 0,05 g/ml	According to ASTM D 1475	
<b>VOC</b>	180 g / l	This value may vary by color	
<b>FLASH POINT</b>	35°C		
<b>MIXING RATIO</b>		Weight	Volume
	<b>Comp. A</b>	100,0	1,0
	<b>Comp. B</b>	90,0	1,0
<b>POT LIFE (25°C)</b>	2 h		
<b>INDUCTION TIME</b>	15 min		
<b>THEORETICAL SPREADING RATE</b>	6,25 m <sup>2</sup> /l - 120 µm		
	2,5 m <sup>2</sup> /l - 300 µm		
<b>WET THICKNESS</b>	160 µm - 400 µm		
<b>DRY THICKNESS</b>	120 µm - 300 µm		
<b>DRYING TIME, for 120 µm</b>		<b>25°C</b>	
		Minimum	Maximum
	<b>Touch</b>		1 h
	<b>Handle</b>		3 h
	<b>Recoat</b>	3 h	
<b>ENVIRONMENTAL CONDITIONS</b>	<b>Temperature</b>	Should be between 0 to 40°C.	
	<b>Relative Humidity</b>	Between 30 to 85%	
	<b>Dew Point</b>	Surface temperature is at least 3°C above dew point	
	<b>Thinner</b>	420.0000	
<b>APPLICATION</b>	<b>Brush</b>	It is not necessary dilution. This method must be used only for retouch and backing of welding cords and corners.	
	<b>Roller</b>	Dilute up to 10% (vol.) with recommended thinner. Need more coats to achieve the desired build. Must be used solvent resistant roller (sheep wool). The wool must be cutted (small size) to avoid blistering during the application.	
	<b>Conventional Spray Gun</b>	Dilute up to 10% (vol.) with recommended thinner. Conventional DeVilbiss JGA 502 EX 67 spray gun or similar. Spray pressure between 3,0 a 4,0 kgf/cm <sup>2</sup> (42 to 56 psi). Tank pressure between 1,5 e 2,5 kgf/cm <sup>2</sup> (21 to 35 psi).	
	<b>AirLess Spray Gun</b>	Dilute up to 10% (vol.) with recommended thinner. Use nozzles between 23 to 29 and pump pressure between 175 to 210 kgf/cm <sup>2</sup> (2500 to 3000 psi).	



---

<b>SURFACE PREPARATION</b>	<b>Direct over carbon steel</b>	The surface must be dry, free of contaminants such as salt deposits, oil, grease, fat, dust, etc. Recommended abrasive blast ISO 8501-1 St 3 (minimum) if the surface is grade of C. If the steel to corrosion mill scale, proceed blasting to Sa 2½.
	<b>Recommended Primers</b>	Not applicable
	<b>Coated Surfaces</b>	The surface must be clean and free of contaminants as oils, fat, grease and dust. Must not present peeling's areas. Proceed light sanding (220) to break the gloss.
<b>Recommended TopCoat</b>		Please consult our technical department.

---

**SHELF LIFE** 12 months

**UN NUMBER** 1263

**HAZARD NUMBER** 33

---

**IMPORTANT RECOMMENDATIONS**

1. The practical spreading rate of the product varies according to the applied thickness, application method and techniques, type and rugosity of the surface and ambient conditions.
2. The weight/l, viscosity and drying values were obtained in laboratory at a temperature of 25°C. At an altered temperature, the results might be different from the specified ones. For temperatures below 10 ° C, contact our technical department.
3. Pot life is shortened by higher temperature and by the increase of catalyzed volume.
4. Low temperatures increase curing time. For temperatures below 10°C, contact our Consultants.
5. If the recoating interval is exceeded, proceed light sanding. For temperatures above the established repainting the range will be reduced.

---

**SAFETY PRECAUTIONS**

1. Improper use and handling of this product can be hazardous to health and cause fire or explosion. Do not use it without first taking all appropriate measures to prevent property damage and injuries.
2. Storage: keep the product in sheltered, well-ventilated areas. Maximum temperature: 40° C. Must not be directly exposed to the sun.
3. Flammable: flammable product, which must be kept distant from ignition sources, and do not smoke nearby.
4. Inhalation: Avoid breathing vapors, keeping proper ventilation during application and drying.
5. Handling: wear proper protective clothing and masks, goggles, etc. Do not eat or drink nor allow children and animals to be near the application area.

---

**HEALTH HAZARDS**

1. Skin contact: wash affected area thoroughly with neutral soap.
2. Clothing contact: remove clothing and wash it.
3. Leakage: Isolate the area, and do not smoke nearby. If large quantity leaked in confined area, wear protective masks. Do not inhale vapors. Stop leakage with sand, sawdust or soil, and transfer liquid and solid to separated recipients for disposal.
4. Fire: protect non-affected recipients with water spray. Extinguish fire using carbon dioxide, foam or dry chemical.
5. Eyes contact: flush eyes with large amounts of clean water for at least 10 minutes, and get medical attention immediately.

**IMPORTANT:** For further information consult the product MSDS (Material Safety Data Sheet).

---